



VIPUL ORGANICS
Interconnected Chemistry
SUNVAT BROWN R M.D[®]

C.I NAME – Vat Brown 3

C.I No : 69015

PROPERTIES

Molecular Weight : 665.65

Hue: Reddish brown Powder

Chemical Family : Anthraquinone

General Properties	Dyeing Method		IN at 60 ^o c	
	Levelling		M	
	Coverage of dead cotton		P	
	Polyster stain		4-5	
Fastness Properties	Light	1/10	7	
		1/10	8	
	Washing ISO 4	Effect	4	
		Stain	4-5	
	Soda Boil	Effect	4	
		Stain	5	
	Bleaching	Sodium Hypochlorite		4-5
		Hydrogen Peroxide	Effect	4 - 5
			Stain	5
	Hot Pressing	Dry	Immediately	4 Y
			After 4 Hours	5
		Wet	Effect	5
			Stain	4-5
	Water Spotting			4 - 5

DYEING.

METHOD **SUNVAT- NORMAL**

Vatting Temp. **55 Deg. Centigrade**

Dyeing Temp. **60 Deg. Centigrade**

Leuco (Alkaline) . **Yellowish brown**

Remark ;

A brown 3 dye with good light fastness properties used for coloration of institutional wear. The product requires thorough soaping to obtain a stable shade. It is available in Micro disperse varieties

Available Forms : Micro Disperse

Packing : 25 kg . Carboys & In Corrugated boxes.



VIPUL ORGANICS

Interconnected Chemistry

SUNVAT BROWN R M. D[®]

DYEING ON YARN



1%

2%

DYEING ON TERRY TOWEL



1%

2%

PADDING ON COTTON FABRIC (20 GPL)

