



VIPUL ORGANICS
Interconnected Chemistry
SUNVAT PINK R M.D[®]

C.I NAME – VAT RED 1

C.I No : 73360

PROPERTIES

Molecular Weight : 393.31

Hue: Red Powder

Chemical Family : Thioindigo

General Properties	Dyeing Method		IN at 60 ^o c	
	Levelling		VG	
	Coverage of dead cotton		M	
	Polyster stain		3-5 R	
Fastness Properties	Light	1/10	6	
		1/10	6-7	
	Washing ISO 4	Effect	4-5	
		Stain	5	
	Soda Boil	Effect	2-3BL	
		Stain	3	
	Bleaching	Sodium Hypochlorite		4-5
		Hydrogen Peroxide	Effect	5
			Stain	5
	Hot Pressing	Dry	Immediately	4-5
			After 4 Hours	5
		Wet	Effect	5
			Stain	5
	Water Spotting			3-4Y

DYEING.

METHOD	SUNVAT- 1
Vatting Temp.	85 Deg. Centigrade
Dyeing Temp.	60 Deg. Centigrade
Leuco (Alkaline) .	Yellow

Remark ;

A bright pink dye used for various shades of pink. The product is available in disperse varieties.

Available Forms : Micro Disperse

Packing : 25 kg . Carboys & In Corrugated boxes.



VIPUL ORGANICS

Interconnected Chemistry

SUNVAT PINK R M. D[®]

DYEING ON YARN



1%

2%

DYEING ON TERRY TOWEL



1%

2%

PADDING ON COTTON FABRIC (20 GPL)

